

# isola

## 370HR

### High Performance Laminate and Prepreg

370HR is the industry's "best in class" lead-free compatible product for high-reliability applications across the telecommunications and high-end automotive markets.

370HR laminates and prepregs are made using a patented high performance 180°C Tg FR-4 multifunctional epoxy resin system that is designed for multilayer Printed Wiring Board (PWB) applications where maximum thermal performance and reliability are required. We manufacture 370HR laminates and prepregs with a patented high performance resin and high quality E-glass glass fabric for superior Conductive Anodic Filament (CAF) resistance. This system provides superior thermal performance with low Coefficient of Thermal Expansion (CTE) and the mechanical, chemical and moisture resistance properties that equal or exceed the performance of traditional FR-4 materials.

370HR is used in thousands of PWB designs and has proven to be best in class for thermal reliability, CAF performance, ease of processing and proven performance on sequential lamination designs.

### Product Attributes

High Thermal Reliability , High Density Interconnect

### Typical Market Applications

Computing, Storage & Peripherals , Consumer Electronics , Networking & Communication Systems , Aerospace & Defense , Medical, Industrial & Instrumentation , Automotive & Transportation

#### ORDERING INFORMATION:

Contact your local sales representative or visit [www.isola-group.com](http://www.isola-group.com) for further information.

Isola Group  
3100 West Ray Road  
Suite 301  
Chandler, AZ 85226  
Phone: 480-893-6527  
Fax: 480-893-1409  
[info@isola-group.com](mailto:info@isola-group.com)

Isola Asia Pacific (Hong Kong) Ltd.  
Unit 3512 - 3522, 35/F  
No. 1 Hung To Road, Kwun Tong,  
Kowloon, Hong Kong  
Phone: 852-2418-1318  
Fax: 852-2418-1533  
[info.hkg@isola-group.com](mailto:info.hkg@isola-group.com)

Isola GmbH  
Isola Strasse 2  
D-52348 Düren,  
Germany  
Phone: 49-2421-8080  
Fax: 49-2421-808164  
[info-dur@isola-group.com](mailto:info-dur@isola-group.com)

High Thermal Reliability

## Data Sheet

Tg 180°C

Td 340°C

Dk 4.04

Df 0.0210

IPC-4101 - /101 /98 /99 /126

UL - File Number E41625

Last Updated June 21, 2017  
Revision No: 3

### Product Features

- Industry Recognition
  - UL File Number: E41625
  - Qualified to UL's MCIL Program
  - RoHS Compliant
- Performance Attributes
  - CAF resistant
- Processing Advantages
  - FR-4 process compatible
  - UV blocking and AOI fluorescence

### Product Availability

- Standard Material Offering: Laminate
  - 2 to 125 mil (0.05 to 3.2 mm)
  - Available in full size sheet or panel form
- Copper Foil Type
  - HTE Grade 3
  - RTF (Reverse Treat Foil)
- Copper Weight
  - ½ to 2 oz (18 to 70 µm) available
  - Heavier copper available
  - Thinner copper foil available
- Standard Material Offering: Prepreg
  - Roll or panel form
  - Tooling of prepreg panels
- Glass Fabric Availability
  - E-glass
  - Square weave glass
  - Mechanically spread glass

# 370HR Typical Values

Last Updated Jun 21, 2017

| Property   | Typical Value  | Units  | Test Method              |  |
|--|--|--|--------------------------|--|
|  |  | Metric (English)                                     | IPC-TM-650 (or as noted) |  |
| Glass Transition Temperature (Tg) by DSC               | 180  | °C   | 2.4.25C                  |  |
| Decomposition Temperature (Td) by TGA @ 5% weight loss | 340  | °C   | 2.4.24.6                 |  |
| Time to Delaminate by TMA (Copper removed)             | A. T260<br>B. T288   | 60<br>30   | Minutes                  | 2.4.24.1   |
| Z-Axis CTE   | A. Pre-Tg<br>B. Post-Tg<br>C. 50 to 260°C, (Total Expansion)   | 45<br>230<br>2.8                                     | ppm/°C<br>ppm/°C<br>%    | 2.4.24C  |
| X/Y-Axis CTE   | Pre-Tg   | 13/14  | ppm/°C                   | 2.4.24C  |
| Thermal Conductivity                                   | —  | —  | W/mK                     | ASTM E1952   |
| Thermal Stress 10 sec @ 288°C (550.4°F)                | A. Unetched<br>B. Etched   | Pass   | Pass Visual              | 2.4.13.1   |
| Dk, Permittivity                                       | A. @ 100 MHz<br>B. @ 1 GHz<br>C. @ 2 GHz<br>D. @ 5 GHz<br>E. @ 10 GHz  | 4.24<br>4.17<br>4.04<br>3.92<br>3.92                 | —                        | 2.5.5.3<br>2.5.5.9<br>Bereskin Stripline<br>Bereskin Stripline<br>Bereskin Stripline |
| Df, Loss Tangent                                       | A. @ 100 MHz<br>B. @ 1 GHz<br>C. @ 2 GHz<br>D. @ 5 GHz<br>E. @ 10 GHz  | 0.0150<br>0.0161<br>0.0210<br>0.0250<br>0.0250       | —<br>—<br>—<br>—         | 2.5.5.3<br>2.5.5.9<br>Bereskin Stripline<br>2.5.5.5<br>2.5.5.5                       |
| Volume Resistivity                                     | A. After moisture resistance<br>B. At elevated temperature   | 3.0 x 10 <sup>8</sup><br>7.0 x 10 <sup>8</sup>       | MΩ-cm                    | 2.5.17.1   |
| Surface Resistivity                                    | A. After moisture resistance<br>B. At elevated temperature   | 3.0 x 10 <sup>6</sup><br>2.0 x 10 <sup>8</sup>       | MΩ                       | 2.5.17.1   |
| Dielectric Breakdown                                   | >50  | >50  | kV                       | 2.5.6B   |
| Arc Resistance   | 115  | 115  | Seconds                  | 2.5.1B   |
| Electric Strength (Laminate & laminated prepreg)       | 54 (1350)  | 54 (1350)  | kV/mm (V/mil)            | 2.5.6.2A   |
| Comparative Tracking Index (CTI)                       | 3 (175-249)  | 3 (175-249)  | Class (Volts)            | UL 746A<br>ASTM D3638  |
| Peel Strength  | A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil]<br>B. Standard profile copper<br>1. After thermal stress<br>2. At 125°C (257°F)<br>3. After process solutions | 1.14 (6.5)<br>1.25 (7.0)<br>1.25 (7.0)<br>1.14 (6.5) | N/mm (lb/inch)           | 2.4.8C<br>2.4.8.2A<br>2.4.8.3<br>2.4.8.3   |
| Flexural Strength                                      | A. Length direction<br>B. Cross direction  | 90,000<br>77,000                                     |                          | 2.4.4B   |
| Tensile Strength                                       | A. Length direction<br>B. Cross direction  | 55,900<br>35,620                                     |                          | ASTM D3039   |
| Poisson's Ratio  | A. Length direction<br>B. Cross direction  | 0.177<br>0.171                                       | —                        | ASTM D3039   |
| Moisture Absorption                                    | 0.15   | 0.15   | %                        | 2.6.2.1A   |
| Flammability (Laminate & laminated prepreg)            | V-0  | V-0  | Rating                   | UL 94  |
| Max Operating Temperature                              | 130  | 130  | °C                       | UL 796   |

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

[www.isola-group.com/products/all-printed-circuit-materials/market/automotive/](http://www.isola-group.com/products/all-printed-circuit-materials/market/automotive/)

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. 370HR is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.

