



S3110

(UL ANSI: CEM-1)

FEATURES

- Lower warpage
- Good thermal resistance
- Good moisture resistance
- Good mechanical process ability

APPLICATIONS

Display,
Power supplier
Game machine
Keyboard, instrument
Household appliances

GENERAL PROPERTIES

Test Items	Test Method	Test Condition	Unit	Typical Value
Thermal Stress	IPC-TM-650 2.4.13.1	288℃, solder float	s	30
Z-axis CTE	IPC-TM-650 2.4.24	50-260℃	%	6.2
Permittivity (1MHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	4.4
Loss Tangent (1MHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	0.022
Volume Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ-cm	7.8×10 ⁸
Surface Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ	5.6×10 ⁷
Arc Resistance	IPC-TM-650 2.5.1	D-48/50+D-0.5/23	s	118
Dielectric Breakdown	IPC-TM-650 2.5.6	D-48/50+D-0.5/23	kV	>45
Peel Strength (1oz)	IPC-TM-650 2.4.8	288℃/10s	N/mm [lb/in]	1.8 [10.28]
Flexural Strength (LW/CW)	IPC-TM-650 2.4.4	A	Mpa	420/358
Water Absorption	IPC-TM-650 2.6.2.1	D-24/23	%	0.13
Flammability	UL94	C-48/23/50	Rating	V-0
CTI	IEC60112	A	Rating	PLC 2

- Remarks:
1. Specification sheet: IPC-4101/10, is for your reference only.
 2. All the typical value is based on the 1.6mm specimen.
 3. All the typical value listed above is for your reference only, please turn to Shengyi Technology Co., Ltd for detailed information, and all rights from this data sheet are reserved by Shengyi Technology Co., Ltd.

PURCHASING INFORMATION

Thickness	Copper foil	Standard size
0.63mm to 3.2mm	18um to 105 um	1,020mm ×1,220mm(40"×48") 915mm ×1,220mm(36"×48") 1,070mm ×1,220mm(42"×48")

Remarks: Other sheet size and thickness could be available upon request.